



Americover PSR 6CC
6 mil Clear String Reinforced Enclosure Film

PROPERTIES	TEST METHOD	Americover PSR 6CC
APPEARANCE		CLEAR
WEIGHT PER MSF		19.5 LBS
THICKNESS (NOMINAL)		6 MIL
ELONGATION @ MAX LOAD %		
DIAGONAL A	ASTM D7003	266 %
DIAGONAL B		370 %
GRAB TENSILE		
DIAGONAL A	ASTM D7004	54 LBS
DIAGONAL B		52 LBS
TRAPEZOIDAL TEAR		
DIAGONAL A	ASTM D4533	51 LBS
DIAGONAL B		37 LBS
HYDROSTATIC RESISTANCE	ASTM D751, PROCEDURE A	36 PSI
WATER VAPOR	ASTM E96	0.337 g/day/m ²
TRANSMISSION		0.014 g/hour/m ²
		0.070 Perms

NOTE: TEST RESULTS WERE COMPILED BY AN INDEPENDENT LABORATORY
RESULTS LISTED ARE THE MEAN RESULTS OF THESE TESTS.

AMERICOVER PSR 6CC IS A CLEAR REINFORCED STRING MATERIAL. THIS MATERIAL IS MANUFACTURED BY PLACING A WEB OF 1,000 DENIER POLYESTER STRING BETWEEN TWO LAYERS OF HIGH STRENGTH POLYTHEYLENE AND THEN LAMINATING THE MATERIAL TOGETHER WITH MOLTEN POLYETHYLENE.

CALL FOR PRICING.

Covering You From The Ground Up

2067 Wineridge Place, Ste. F • Escondido, CA 92029 • 800-747-6095 • 760-747-6095 • fax 760-747-1920

www.americover.com