



Americover PSR 6FR
6 mil Fire Retardant
String Reinforced Enclosure Film

PROPERTIES	TEST METHOD	Integra SRP 6FR
APPEARANCE		YELLOW
WEIGHT PER MSF		21.5 LBS
THICKNESS (NOMINAL)		6 MIL
ELONGATION @ MAX LOAD % DIAGONAL A DIAGONAL B	ASTM D7003	397 % 272 %
GRAB TENSILE DIAGONAL A DIAGONAL B	ASTM D7004	66 LBS 74 LBS
TRAPEZOIDAL TEAR DIAGONAL A DIAGONAL B	ASTM D4533	44 LBS 43 LBS
HYDROSTATIC RESISTANCE	ASTM D751, PROCEDURE A	40 PSI
MAXIMUM USE TEMP MINIMUM USE TEMP		180 F - 70 F
WATER VAPOR TRANSMISSION	ASTM E96	.681 g/day/m ² .028 g/hour/m ² .098 Perms
FLAME SPREAD INDEX	ASTM E84	5
SMOKE DEVELOPED INDEX	ASTM E84	20

NOTE: TEST RESULTS WERE COMPILED BY AN INDEPENDENT LABORATORY
RESULTS LISTED ARE THE MEAN RESULTS OF THESE TESTS.

AMERICOVER PSR 6FR IS A YELLOW REINFORCED **FIRE RETARDANT** STRING MATERIAL. THIS MATERIAL IS MANUFACTURED BY PLACING A WEB OF 1,000 DENIER POLYESTER STRING BETWEEN TWO LAYERS OF HIGH STRENGTH POLYTHEYLENE AND THEN LAMINATING THE MATERIAL TOGETHER WITH MOLTEN POLYETHYLENE.

CALL FOR PRICING.