

# ASFR6

6 MIL ANTI-STATIC, FIRE RETARDANT POLY



## PRODUCT DESCRIPTION

ASFR6 is a 6 mil, fire retardant, anti-static film. This specialized plastic sheeting was originally designed to meet the regulations of the telecommunications industry. Therefore, it conforms to regulations dated October 1, 2001, Section B, TP 76300MP 1.2.7: "All combustible materials stored overnight in the equipment area shall be completely covered with a fire retardant tarp that meets the NFPA 701 or UL214 and is clearly marked as such".

## PRODUCT

## PART NUMBER

Anti-Static Fire Retardant 6 mil .....ASFR6

## PRODUCT USE

This 6 mil polyethylene is printed with the fire retardant standard and is suitable for indoor and outdoor use.

## APPLICATIONS

- Can be used to cover a variety of surfaces including electronic equipment
- Enclosure film for Hospitals and schools

# ASFR6

6 MIL ANTI-STATIC, FIRE RETARDANT POLY

PROPERTIES	TEST METHOD	VALUES
Thickness	-	6 mil
Tear Strength	ASTM D1922	Machine Direction: 1,000 grams Transverse Direction: 2,000 grams
Tensile Strength	ASTM D882	Machine Direction: 3,000 psi Transverse Direction: 3,000 psi
Ultimate Elongation	ASTM D882	Machine Direction: 600 Transverse Direction: 600
Dart Impact	ASTM D1709	400 grams
Surface Resistivity	ANSI/EOS/ESD-S11.11	10 <sup>12</sup> max ohms/sq
Flammability	NFPA 701	Pass



The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, express or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

Scan for our mobile app

