

# BOLD™

BLACKOUT LIGHT DEPRIVATION GREENHOUSE COVER



## PRODUCT

## PART NUMBER

BOLD ..... BOLD 8WB



Photo: Ed Rosenthal

## APPLICATIONS

- Light Deprivation Covers
- Greenhouse Covers

## PRODUCT DESCRIPTION

The ONLY lightweight, reinforced light deprivation tarp that consists of two sheets of high strength virgin polyethylene film laminated together with a third layer of molten polyethylene. The white outer layer contains UV inhibitors and thermal stabilizers and the black outer layer contains carbon black to enhance outdoor life and ensure total light deprivation. The white outer layer is also designed to reduce heat build-up and condensation. A heavy scrim reinforcement placed between these plies greatly enhances tear resistance and increases service life. Heavy-duty diamond reinforcement responds to tears immediately by surrounding and stopping the tear.

## PRODUCT USE

Americover's BOLD Cover is significantly stronger and more tear resistant than a standard 8 mil poly film. The extrusion lamination process and high strength reinforcement scrim make this film exceptionally strong yet lightweight.

## SIZE & PACKAGING

Standard rolls sizes are:

- 13.5'X100'
- 26.5'X100'
- 33'X50'
- 33'X100'
- 40'X50'
- 40'X100'
- 46.25'X100'
- 52.75'X100'

Custom sizes available to meet your specifications.

Color: Black/White


**WWW.AMERICOVER.COM**

Email: [sales@americover.com](mailto:sales@americover.com)

Toll Free: 1 800 747 6095

Tel: 1 760 747 6095

Fax: 1 760 747 1920



PROPERTIES	TEST METHOD	PSR - BOLD
Appearance	-	Black/White
Weight Per MSF (lbs)	-	40
Elongation at Max Load % Diagonal A Diagonal B	ASTM D7003	609% 625%
Grab Tensile (lbs) Diagonal A Diagonal B	ASTM D4533	51 48
Temperature	-	-70°F to 150°F
Hydrostatic Resistance	ASTM D751, Procedure A	75 psi
Water Vapor Transmission	ASTM E96	0.0395 perms

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, express or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

Americover®

Scan for our mobile app



**AMERICOVER INC**  
2067 Wineridge Place, Suite. F  
Escondido, CA 92029