

Geo-Shield

HDPE Smooth

Geo-Shield High Density Polyethylene is produced from virgin polyethylene resins. **Geo-Shield** HDPE has outstanding chemical resistance, mechanical properties, environmental stress crack resistance, dimensional stability, and thermal aging characteristics. **Geo-Shield** HDPE contains approximately 97.5% polymer and 2.5% carbon black, antioxidants and heat stabilizers, and contains no other additives, fillers or extenders. **Geo-Shield** HDPE has excellent UV resistance. **Geo-Shield** HDPE does not contain plasticizers that can migrate to the surface, causing premature aging. Manufactured from virgin polyethylene resins, it is designed to provide a high quality, economical geomembrane.

Properties	Test Method	Typical Average Roll Values			
Color		Black	Black	Black	Black
Thickness, mils - Nominal	ASTM D5199	12	20	30	40
Density, gram/cm ³ - Minimum	ASTM D1505	.94	.94	.94	.94
Tensile Properties – Each Direction					
Tensile Strength at Break, lbs/in width (N/mm)	ASTM D6693 Type IV	48 (8)	80 (14)	122 (21)	162 (28)
Tensile Strength at Yield, lbs/in width (N/mm)	Dumbell, 2 ipm	24 (4)	40 (7)	63 (11)	84 (15)
Elongation at Break, %	G.L. 2.0 in	700	700	700	700
Elongation at Yield, %	G.L. 1.3 in	13	13	13	13
Tear Resistance, lbs. (N)	ASTM D1004	8 (35)	13 (60)	21 (93)	28 (125)
Puncture Resistance, lbs. (N)	ASTM D4833	18 (80)	31 (137)	48 (213)	64 (284)
Carbon Black, % minimum	ASTM D1603	2	2	2	2
Carbon Black Dispersion	ASTM D5596	Note (1)	Note (1)	Note (1)	Note (1)
Oxidative Induction Time, Minutes	ASTM D 3895 200 ^o C, O ₂ , 1 atm	>100	>100	>100	>100

Note 1: 9 of 10 views shall be category 1 or 2. No more than 1 view from category 3.

This data is provided for informational purposes only. Americover makes no warranties as to the suitability or the fitness for a specific use or merchantability of products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Americover for current updates.



2067 Wineridge Place, Ste. F • Escondido, CA 92029
 800-747-6095 • 760-747-6095 • Fax 760-747-1920
 www.americover.com