

# TEMPORARY COVER

6 & 10 MIL CLEAR REINFORCED TEMPORARY, EMERGENCY COVER



#### PRODUCT DESCRIPTION

6 & 10 mil mil reinforced temporary covers consist of two sheets of high strength virgin polyethylene film laminated together with a third layer of molten polyethylene. A heavy-duty scrim reinforcement placed between these plies greatly enhances tear-resistance and increases service life. 6 & 10 mil reinforced temporary covers heavy-duty diamond reinforcement responds to tears immediately by surrounding and stopping the tear.

### **APPLICATIONS**

- Seasonal Greenhouse Cover
- Overwintering Cover
- ► Temporary Liners or Covers
- ► Erosion Control
- Sterilization Cover

## PART#

6 MIL CLEAR......D52 10 MIL CLEAR......D510HUV

### PRODUCT USE

6 mil reinforced temporary covers are used for temporary applications that require a lightweight yet highly tear-resistant film such as building enclosures.

10 mil reinforced temporary covers are used in applications that require good outdoor life and demand high puncture and tear strengths. The two outer layers of our 10 mil reinforced temporary covers contain high concentrations of UV inhibitors and thermal stabilizers to assure added outdoor life up to approximately one year.

## **SIZE AND PACKAGING**

6 mil reinforced temporary covers stock sizes are 6, 8, 10, 12, 16, 20, 24, 32, 40 and 60 feet wide and 100 feet long.

10 mil reinforced temporary covers is available in 6 & 20 feet wide by 100 feet long.

All panels are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time saving installation. Custom sizes are available.



## TEMPORARY COVER

**SPECIFICATIONS** 

		6 mil		10 mil	
PROPERTIES	TEST METHOD	IMPERIAL	METRIC	IMPERIAL	METRIC
Appearance		Colorless		Colorless	
Thickness/Nominal		6 mil	0.15 mil	10 mil	0.25 mil
Weight		17 lbs/MSF 2.4 oz/yd²	83 g/m²	41 lbs/MSF 5.9 oz/yd²	200 g/m²
Construction		Extrusion laminated with scrim reinforcement			
<sup>1</sup> 1" Tensile Strength	ASTM D7003	53 lbf/in	93 N/cm	60 lbf/in	105 N/cm
<sup>2</sup> Elongation at Film Break	ASTM D7003	493 %	493 %	500 %	500 %
Grab Tensile	ASTM D7004	60 lbf	267 N	80 lbf	356 N
*Trapezoid Tear	ASTM D4533	32 lbf	142 N	55 lbf	245 N
Mullen Burst	ASTM D751	34 psi	234 kPa	90 psi	621 kPa
Maximum Static Use Tempera- ture		180°F	82°C	180°F	82°C
Minimum Static Use Tempera- ture		-70°F	-57°C	-70°F	-57°C
WVTR	ASTM E96 Procedure B	0.587 grains/(ft²·hr)	0.591 g/(m²·day)	0.214 grains/(ft²·hr)	0.215 g/(m²·day)
Perm Rating	ASTM E96 Procedure B	0.086 Perms grains/(ft²·hg)	0.057 g/(24hr·mm²·hg)	0.031 Perms grains/(ft²·hg)	0.021 g/(24hr·mm²·hg)

<sup>&</sup>lt;sup>1</sup> Tests are an average of diagonal directions.

6 mil reinforced temporary cover is a clear four layer reinforced extrusion laminate. The outer layers consist of a clear high-strength polyethylene film. 6 mil reinforced temporary cover is reinforced with a heavy duty scrim laid in a diagonal pattern spaced 3/8" apart with an additional machine direction scrim every 9" across the width. The individual plies are laminated together with molten polyethylene.

10 mil reinforced temporary cover is a clear, four-layer reinforced extrusion laminate. The outer layers consist of a high strength polyethylene film with a high concentration of U.V. and thermal stabilizers. 10 mil reinforced temporary cover is reinforced with a minimum of a 1000 denier scrim laid in a diagonal pattern spaced 3/8" apart with an additional machine direction scrim every 3" across the width. The individual plies are laminated together with molten polyethylene.

NOTE: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. AMERICOVER, INC. MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.americover.com

AG.121014.121417



800.747.6095 760.747.6095





<sup>&</sup>lt;sup>2</sup> Tests are an average of primary reinforcement directions