



ENKADRAIN® 3615R

BUILDING 3D MATS - 3D DRAINAGE

PRODUCT DESCRIPTION

Enkadrain® 3615R is one of a new generation of environmentally conscious Enkadrain® products. This drainage composite consists of a post-industrial recycled polypropylene drainage core of fused, entangled filaments and a geocomposite fabric bonded to one side. The entangled filaments are molded into a square waffle pattern that maintains the flexible design of other Enkadrain® products. This product, because it exceeds 40% post-industrial recycled content, can help contribute up to 2 LEED points, when used in conjunction with other recycled content products. Enkadrain® 3615R can contribute towards additional LEED points when used with a green roof by reducing stormwater runoff, heat islands and energy consumption.

FEATURES & BENEFITS

- ▶ Excellent durability
- ▶ Continuous flow in all directions, even under high loads
- ▶ Conforms to irregular surfaces and corners with complete and effective coverage
- ▶ Long rolls reduce installation costs by eliminating interlocking and excessive seams
- ▶ Protects waterproofing during and after backfill
- ▶ Waffle design creates open flow path – even during backfill
- ▶ Recycled content polymer contributes towards LEED points
- ▶ Increased flow rates over same thickness nylon and HDPE drains
- ▶ 3” fabric overlap flap

APPLICATIONS

- ▶ Foundation walls
- ▶ Green roofs
- ▶ Plaza decks
- ▶ Retaining walls
- ▶ Beneath slabs
- ▶ Earth sheltered homes
- ▶ Underground parking
- ▶ Exterior planters

PHYSICAL PROPERTIES

Property	Imperial	Metric
Core Material	Recycled PP	
Total Weight (avg.)	28.5 oz/yd ²	966.4 g/m ²
Core Thickness	0.45 in	11.43 mm
Core Weight (avg.)	24.0 oz/yd ²	813.8 g/m ²

POLYMER PROPERTIES

Polypropylene has excellent resistance to organic solvents, degreasing agents, acids, and alkalines. It has tensile strength superior to high density polyethylene. It has a low moisture absorption rate, is resistant to staining, and is very light weight.

FLOW RATES

Pressure	1.0 Gradient	0.5 Gradient	0.2 Gradient
250 psf	21.0 gal/min/ft	14.5 gal/min/ft	9.6 gal/min/ft
500 psf	21.0 gal/min/ft	13.8 gal/min/ft	8.2 gal/min/ft
1000 psf	19.7 gal/min/ft	13.0gal/min/ft	8.0 gal/min/ft
2000 psf	19.0 gal/min/ft	14.1 gal/min/ft	8.0 gal/min/ft
3000 psf	18.9 gal/min/ft	13.2 gal/min/ft	7.7 gal/min/ft
3600 psf	18.9 gal/min/ft	12.9 gal/min/ft	7.5 gal/min/ft
5000 psf	18.1 gal/min/ft	12.2 gal/min/ft	7.5 gal/min/ft
8000 psf	11.1 gal/min/ft	7.1 gal/min/ft	4.1 gal/min/ft

Typical flow vs. pressure for vertical applications (ASTM D-4716)
Sample configuration: Plate/Enkadrain®/Plate

PACKAGING

PROPERTY	IMPERIAL	METRIC
Core Width	39.0 in	99.1 cm
Length	100 ft	30.5 m
Area	36 yd ²	30.1 m ²
Roll Diameter	27.0 in	68.7 cm
Gross Roll Weight	77 lbs	34.9 kg

FABRIC PROPERTIES

PROPERTIES	TEST METHOD	IMPERIAL	METRIC
Polymer		PP	
Fabric Color		Black	
Weight	ASTM D-5261	4.5 oz/yd ²	152.6 g/m ²
Grab Strength	ASTM D-4632	120.0 lbs	0.54 kN
Grab Elongation	ASTM D-4632	50%	50%
Trapezoidal Tear	ASTM D-4533	50 lbs	0.22 kN
Puncture Resistance	ASTM D-4833	70 lbs	0.31 kN
AOS (maximum average)	ASTM D-4751	70 US Sieve	0.212 mm
Flow Rate	ASTM D-4491	120.0 gal/ min/sq.ft	4887 1/sec/ sq. m
Permittivity	ASTM D-4491	1.8 sec ⁻¹	1.8 sec ⁻¹

NOTE: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. AMERICOVER, INC. MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.Americover.com

LB 3619