



BOLD®

8 MIL REINFORCED BLACKOUT LIGHT DEPRIVATION TARP



PRODUCT DESCRIPTION

BOLD® consists of two sheets of high strength virgin polyethylene film laminated together with a third layer of molten polyethylene. The white outer layer contains UV inhibitors and thermal stabilizers to reduce heat build-up and condensation. The black outer layer contains carbon black to enhance outdoor life and ensure total light deprivation. A heavy-duty diamond reinforcement scrim placed between these plies greatly enhances tear resistance and increases service life. This lightweight cover is designed to last through more harvests than non-reinforced films.

APPLICATIONS

- ▶ Light deprivation cover
- ▶ Auto light dep cover for greenhouses
- ▶ Blackout cover
- ▶ Growbed liner
- ▶ Reflective liner

PRODUCT USE

BOLD® can withstand daily covering and uncovering for multiple seasons for both manually operated and automated greenhouse systems.

SIZE AND PACKAGING

WIDTH	LENGTH	WIDTH	LENGTH(S)	WIDTH	LENGTH(S)
13.5'	100'	33'	50' 75' 100' 125'	46.5'	100' 125'
26.5'	100'	40'	50' 75' 100'	52.75'	100' 125'

Custom **Lengths** start at 50' and increase in 5' increments up to 500' long

All panels are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time saving installation.

PROPERTIES	TEST METHOD	Black/White
Weight Per MSF (lbs)	-	39 lbs
Elongation at Max Load % Diagonal A Diagonal B	ASTM D7003	609% 325%
Grab Tensile (lbs) Diagonal A Diagonal B	ASTM D4533	51 48
Temperature	-	-70°F to 150°F
Hydrostatic Resistance	ASTM D751, Procedure A	75 psi
Water Vapor Transmission	ASTM E96	0.0395 perms

NOTE: The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, express or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

RI.121014.1022018