



DURA-SKRIM® 12BB & 12WB

FOUR-LAYER REINFORCED EXTRUSION LAMINATE



PRODUCT DESCRIPTION

DURA-SKRIM® 12BB and 12WB consist of two sheets of high-strength polyethylene film laminated together with a third layer of molten polyethylene. The white outer layer (DURA-SKRIM® 12WB) contains UV inhibitors and thermal stabilizers and the black outer layer(s) contains carbon black to enhance outdoor life. The white outer surface is also designed to reduce heat build up and condensation. A heavy-duty scrim reinforcement placed between these plies greatly enhances tear and puncture resistance and increases service life. DURA-SKRIM® is reinforced with a high strength scrim reinforcement laid in a diagonal pattern spaced 3/8" apart for uniform tear resistance in both machine and transverse directions.

APPLICATIONS

- ▶ Cargo Coverings
- ▶ Interim Landfill Covers
- ▶ Daily Landfill Covers
- ▶ Temporary Erosion Control
- ▶ Divider Curtains
- ▶ Crawlspace Encapsulation
- ▶ Remediation Covers or Liners
- ▶ Pit/Pond Liners
- ▶ Underslab Vapor Retarders
- ▶ Temporary Earthen Liners
- ▶ Temporary Rainshed Covers

PRODUCT USE

DURA-SKRIM® 12BB and 12WB are used in more demanding applications requiring high tear resistance. Please inquire about DURA-SKRIM® 8BV and 12BV for longer-term applications up to 5 years, meeting GRI-GM22 Standard Specifications for Scrim Reinforced Geomembranes Used in Exposed Temporary Applications.

SIZE AND PACKAGING

DURA-SKRIM® 12BB and 12WB, are available in a variety of widths up to 120,000 square feet. All panels are manufactured in a quality controlled environment and are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time-saving installation.



DURA-SKRIM®

SPECIFICATIONS

PROPERTIES	TEST METHOD
Appearance	
Thickness/Nominal	ASTM D5199
Weight	ASTM D751
Construction	Extrusion laminated with scrim reinforcement
² Grab Tensile Strength	ASTM D7004
² Grab Tensile Elongation	ASTM D7004
³ Tongue Tear	ASTM D5884
CBR Puncture Resistance	ASTM D6241
Mullen Burst	ASTM D751
WVTR	ASTM E96
Perm Rating	ASTM E96
Hydraulic Conductivity	ASTM E96
Maximum Static Use Temperature	
Minimum Static Use Temperature	

² Tests are an average of primary reinforcement directions.

³ Tests are an average of machine and transverse directions.

DURA-SKRIM® 12BB and 12WB consist of two sheets of high-strength polyethylene film laminated together with a third layer of molten polyethylene. The white outer layer (DURA-SKRIM® 12WB) contains UV inhibitors and thermal stabilizers and the black outer layer(s) contains carbon black to enhance outdoor life. The white outer surface is also designed to reduce heat build up and condensation. A heavy-duty scrim reinforcement placed between these plies greatly enhances tear and puncture resistance and increases service life. DURA-SKRIM® is reinforced with a high strength scrim reinforcement laid in a diagonal pattern spaced 3/8" apart for uniform tear resistance in both machine and transverse directions.

DURA-SKRIM® 12BB / 12WBK	
IMPERIAL	METRIC
Black/Black or White/Black	
12 mil	0.30 mm
55 lbs/MSF	269 g/m ²
Extrusion laminated with scrim reinforcement	
100 lbs	445 N
17 %	17 %
40 lbs	178 N
250 lbs	1112 N
100 psi	690 kPa
0.010 grains/ft ² •hr	0.167 g/m ² •day
0.023 Perms	0.015 g/m ² •day•mm Hg
3.14x10 ⁻¹⁰ cm/sec	
180° F	82° C
-70° F	-57° C

NOTE: The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, express or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

RI.062817.020518

800.747.6095
760.747.6095



Inquiries@americover.com
www.americover.com

2067 Wineridge Place, Suite F • Escondido, CA 92029

