



REINFORCED SEAMING TAPE

STRING REINFORCED POLYETHYLENE BACKING SEAMING TAPE



PRODUCT DESCRIPTION

Reinforced Seaming Tape is a string reinforced polyethylene film with a 10 mil, hot-melt, pressure-sensitive bonding side. A silicone-coated paper release liner makes it easy to install. Reinforced Seaming tape is perfect for applications with exposure to high temperature and/or moisture. Reinforced Seaming Tape is highly tear and puncture resistant.

APPLICATIONS

- ▶ Under slab
- ▶ Walls & roofs
- ▶ Crawl spaces
- ▶ Repair reinforced covers and liners

PRODUCT USE

Reinforced Seaming Tape is ideal for film repairs and seaming panels of vapor barrier or plastic sheeting together. To ensure a secure seal for the initial bond, the application surface should be clean and dry of dirt, dust and moisture. Optimum adhesion occurs when the application surface is above 50° - 60°F. The use of an industrial style hot air blower may be required when attempting to install tape at temperatures below 32°F.

SIZE AND PACKAGING

This tape is available in White, Clear or Black in 4" x 50' rolls.

PROPERTIES	U.S. VALUE	METRIC VALUE
Standard Weight 4" x 50' Roll	3.0 LBS	1.4 KG
Adhesive Thickness	20 mil	0.51 MM
Peel Strength*	55 LBF	244.6 N
Room Temperature ~ 20 hrs (180° Peel)	10.0 - 14.0 LBS/in	44.5 - 62.2 N
Room Temperature ~ Quick Set (180° Peel)	8.5 - 12.5 LBS/in	37.8 - 55.6 N
Softening Temperature (Ring and Ball)	245° - 270° F	-136° - 150° C

* Values obtained when using Polypropylene plates.

NOTE: The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, express or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

RFI.010113.061818